

E-Z PATCH[®]

23

E-Z
JOINT
SEAL[®]

**Self -
Leveling
Expansion
Joint
Sealant**

- *No Mixing**
- *Low Odor**
- *Surface Dries in ½ - 2 Hours**
- *Non-Shrinking**
- *100% Silicone Rubber**

NET 10 U.S. FL. OZ. (296 ML)

- **NO MIXING OR PRIMER NEEDED**
- **NO TOOLING NEEDED**
- **EXCELLENT SELF-LEVELING**
- **U-V LIGHT STABLE**
- **50 YEAR LIFE EXPECTANCY**

***Depth of sealant should be
1/3 to 1/2 the width of joint
(1/4" min. depth)**

***Coverage for a 1/2" wide joint
with 1/4" depth is 12 Ln. Ft.**

E-Z DIRECTIONS:

- Cut down or remove old existing expansion joint (if any).
- Surface must be clean and dry. Remove any old sealant, old paint, oil, grease or soap.
- Can be installed in temperatures as low as 0 degree Fahrenheit.
- Fill the joint to desired depth with dry silica sand or polyethylene backer rod.
- Seal ends of joint and any side cracks, etc. with cement or caulking prior to installing E-Z PATCH® 23.
- Cut tip to desired size and puncture inner foil seal thoroughly.
- Apply E-Z PATCH® 23 evenly in the expansion joint finishing 1/8" below level of concrete surface.
- When finished, seal tip and store remainder of cartridge upright.
- Clean up with paper towel (and mineral spirits or rubbing alcohol if desired).
- Protect from rain for 2 hours.
- Allow 12 hours curing before foot traffic and 48 hours for automobiles.

PRODUCT IS NON-PAINTABLE

CAUTION: DO NOT TAKE INTERNALLY. IF INGESTED, DO NOT INDUCE VOMITING AND CALL A PHYSICIAN IMMEDIATELY. IN CASE OF CONTACT WITH EYES, IMMEDIATELY FLUSH WITH WATER FOR 15 MIN. IF IRRITATION PERSISTS, GET MEDICAL ATTENTION. UNCURED PRODUCT MAY IRRITATE THE SKIN. TO CLEAN FROM SKIN, USE PAPER TOWEL (AND MINERAL SPIRITS OR RUBBING ALCOHOL IF DESIRED) AND THEN WASH SKIN WITH SOAP AND WATER.

-KEEP OUT OF THE REACH OF CHILDREN-

E-Z PRODUCTS

1-888-439-7282

www.e-zpatch.com

