

E-Z PATCH[®] 9

BLUE/GREY PEBBLE POOL PLASTER REPAIR KIT

A EASY TO USE REPAIR KIT THAT LOOKS LIKE ORIGINAL PEBBLE PLASTER

E-Z PRODUCTS

888-439-7282

NET WT. 50 LB. (22.7 Kg)

**REPAIR KIT CONTAINS 32 fl. OZ. (.9 liter) LIQUID CEMENT BONDER
AND APPROX. 50 LB. (22.7 Kg) DRY CEMENT MIX
COVERAGE: APPROX. 15 SQ. FT. (3/8" DEEP)**

E-Z INSTRUCTIONS:

1. Lower water below repair area. 2. Remove loose cement and chip area down at least 3/8" deep. Clean surface. 3. Add 1 oz. of LIQUID CEMENT BONDER per 1½ lb. of **E-Z PATCH 9** DRY CEMENT MIX. Add water and mix until you get the consistency of "mashed potatoes". Use warm water for faster set and cold water to slow set. 4. Firmly trowel **E-Z PATCH 9** filling the area. Trowel again (not as firmly) flat and smooth. Remove excess from edges with a moist sponge. 5. After patch slightly stiffens, lightly spray with water using a hand spray bottle, a bug sprayer or a water hose to expose the pebble. To match very small "mini pebble", do not rinse as much. 6. FOR CRACK REPAIRS: Cut crack 3/8" wide & 3/8" deep, clean surface, rub **E-Z PATCH 9** into area & remove excess with a moist sponge. 7. If there is any residue "haze" the next day, it can be removed by wetting the surface with water & pouring a mixture of 1/3 muratic acid to 2/3 water on the patched area. Wait 1 minute and rinse using a waterhose.

You may refill water the next day

View our instructional repair video showing how to do this repair at www.e-zpatch.com

WARNING: CONTAINS CEMENT, AN ALKALINE SUBSTANCE IRRITATING TO EYES AND SKIN. CONTAINS ACRYLIC RESIN CEMENT BONDER. SHOULD PRODUCT CONTACT EYES, FLUSH THEM IMMEDIATELY AND REPEATEDLY WITH WATER AND CALL A PHYSICIAN. DO NOT TAKE INTERNALLY. IN CASE OF SKIN CONTACT, RINSE IMMEDIATELY WITH WATER. USE OF RUBBER GLOVES IS RECOMMENDED.

KEEP OUT OF THE REACH OF CHILDREN

MADE IN THE U.S.A.

